

# Vivacolor LH

## Lightweight filler

- Waterborne
- Ready to use
- Fast drying
- Easy application and leveling
- Effortless sanding



TECHNICAL DATA		
<b>Fields of application</b>	Indoor walls and ceilings in dry premises. Suitable for filling joints and smoothing plaster concrete, brick, gypsum board and primed fiberboard surfaces, also for filling cracks and holes. To achieve smoother surface overcoat with <i>Vivacolor LF</i> fine filler as last coat.	
<b>Binder</b>	Acrylic copolymer	
<b>Filler</b>	Dolomite, microspheres	
<b>Max particle size</b>	0,2 mm	
<b>Max layer thickness</b>	4 mm	
<b>Adhesion</b>	0,90 N/mm <sup>2</sup>	
<b>Colour</b>	Light grey	
<b>Coverage (per coat)</b>	1mm thin coat plastering: ~ 1 l/m <sup>2</sup> , filling joints and screw holes (2x): ~ 0,25 l/m <sup>2</sup>	
<b>Application method</b>	To be applied with spatula	
<b>Drying time</b>	(at +23 °C, relative air humidity (RH) 50%) 1 mm 3 hours (Drying time is strongly dependent on ambient temperature and relative air humidity)	
<b>Cleaning of painting tools</b>	Water	
<b>Storage</b>	Protect the product from frost!	
<b>Storage time</b>	In tightly closed original container 2 years from production date (stated on can).	
<b>Solid content</b>	About. 62 % m/m.	
<b>Density</b>	About 1,1 kg/l (ISO 2811) .	



<b>Packaging</b>	10 L can; 15L plastic bag	
------------------	---------------------------	--

The data above are verified and correct and based on the laboratory tests held as well as on practical experience. Our management system is certified against international standards ISO 9001 and ISO 14001. As a producer, we cannot be held responsible for any losses incurred upon non-compliance with the technical data sheets or application terms for a particular product. AS TIKKURILA Liimi 5, 10621 Tallinn, Estonia, tel +372 650 11 11, fax +372 650 11 22, e-mail: info.ee@tikkurila.com



## INSTRUCTIONS FOR USE

### PREPARATION

#### Unpainted surfaces:

Clean the surface from dust and dirt. Wash greasy surfaces with cleansing agent *Special Clean*, rinse with water and allow to dry. Prime weak and dusty surfaces with alkyd primer.

#### Previously painted surfaces:

Clean the surface from residues of old paint, dust and dirt. Wash greasy or previously painted surfaces with cleansing agent *Special Clean*, rinse with water and allow to dry. Sand the glossy surfaces of old paint to matt finish, remove dust. Prime weak and dusty surfaces with alkyd primer.

### APPLICATION CONDITIONS

Surface should be clean and dry, temperature of ambient air should be above +5 °C, and relative air humidity should be lower than 80%. Avoid draught and high temperatures during application.

### APPLICATION

Apply filler with spatula. Cracks should be covered with paper or glass-fiber ribbon before filling. If needed sand filled surface when it is dried, remove dust. Eye protection and dust mask are recommended when sanding. Apply second layer of filler when needed.

### CLEANING OF TOOLS

Clean painting instruments from liquid filler residue, then wash with water

### ENVIRONMENTAL, SAFETY AND WASTE REGULATORY

Do not discharge the product into sewerage systems, watercourse, nor pour it onto the ground.

Dry and empty containers should be discarded in compliance with the local regulations.

<b>CE</b>	
AS Tikkurila, Liimi 5, 10621 Tallinn, Estonia	
13	
No. VC-13-01b	
EN 15824:2009	
Internal plaster based on organic binders	
Reaction to Fire	A2-s1,d0
Release of dangerous substances	NPD
Adhesion:	≥ 0,30 MPa

<b>CE</b>	
AS Tikkurila, Liimi 5, 10621 Tallinn, Estonia	
13	
No. VC-13-01a	
EN 13963:2005	
Jointing material for gypsum plasterboards- type 2A	
Reaction to Fire	A2-s1,d0
Release of dangerous substances	NPD
Flexural strength:	> 320N

### TRANSPORTATION

Protect from frost!

### ADDITIONAL PRODUCT INFORMATION

[www.vivacolor.ee](http://www.vivacolor.ee)